

## TALC 10EPG

### A High Impact Strength Imparting Talc


#### Physical Properties

Brightness	90 % +/- 0.5%
Whiteness	92 % +/- 0.5%
Retention on 500#	0.5% Max
Specific Gravity	2.70
Moisture	0.10 %
Bulk Density	0.35 +/- 3
Oil Absorption	44 +/- 3 ML
Refractive Index	1.57
LOI	< 8.0%
Appearance	Free Flowing Dry Powder
SiO <sub>2</sub>	50 - 63%
MgO	20 - 31%
CaO	5 - 1%
Al <sub>2</sub> O <sub>3</sub>	10 - 0.5%
Fe <sub>2</sub> O <sub>3</sub>	<0.1%

#### Particle Size Analysis

D-97	10.0 μ
D-50	2.5 μ

Sedigraph III V1.03  
 Stokes Sedimentation and Beer's Law



The information contained in this Technical Data Sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process. The information provided herein is based on technical data that Next Generation Fillers believes to be reliable, however Next Generation Fillers makes no representation or warranty as to the completeness or accuracy thereof and Next Generation Fillers assumes no liability resulting from its use or for any claims, losses, or damages of any third party.

Recipients receiving this information must exercise their own judgement as to the appropriateness of its use, and it is the users responsibility to assess the materials suitability (including safety) for a particular purpose prior to such use.